

Starting Formulation



Coating 03010: High gloss clear coat for exterior wood

Based on OxyMul 50 AQ-40

Raw material	Grams	Function	Producer
OxyMul 50 AQ-40	977	Alkyd resin emulsion	Ligno Ferox
Borchers Oxycoat	2	Drying catalyst	Borchers
Acrysol RM-2020E	20	HEUR thickener	Dow
Tri-Ethyl-Amine	1	Neutralising agent	Moller Chemie

Total: 1000

Density: 1030 grams / liter
Solids: 40% m/m
pH: 8,8

VOC: 20 grams/ liter
Gloss: 80% at 20° angle
PVC: 0%

The user is held to check quality, safety and other properties of the product referred to herein. The information and the recommendations in this document are to the best of our knowledge, reliable. However, no rights whatsoever can be derived from this document or the information contained therein by any party, other than those expressly accepted by Ligno Ferox in a binding sale and purchase agreement for product referred to herein. For the avoidance of doubt Ligno Ferox makes no warranty of any kind, express or implied, including those of merchantability and fitness for purpose. Unless explicitly agreed to otherwise in writing by Ligno Ferox, all offers, quotations, sales and deliveries of LignoFerox products are subject to its General Conditions of Sale (www.lignoferox.com)